

Sound absorption coefficient according to UNE-EN ISO 354, UNE-EN ISO 11654, ASTM C 423

Determination of sound absorption coefficients

Manufacturer : Skum Acoustics SL
Brand : Skum Acoustics

Product ref. : RÖR
Date : 8.01.2018

Description of the acoustic element :



Material : BTECT-W (melamine resin)
Thickness [mm] : -
Notes : reticle : 6 x 4 (gap 100mm)

Format [mm] : 800 x ø 150
Color : White - RAL 9016

Evaluation : Reverberation time
Other values obtained by engineering method

Frequency [Hz]	Absorption coeff. α_s	Equiv. Area A
100	0,20	2,38
125	0,23	2,74
160	0,24	2,86
200	0,35	4,17
250	0,44	5,24
315	0,58	6,90
400	0,79	9,40
500	0,84	10,00
630	0,95	11,34
800	0,99	11,83
1.000	1,03	12,20
1.250	1,00	11,90
1.600	1,03	12,20
2.000	1,08	12,81
2.500	1,09	12,93
3.150	1,06	12,61
4.000	1,02	12,14
5.000	1,01	12,02

NRC	0,85
SAA	0,85
α_w	0,75(MH)
Sound Absorption Class accord. to UNE-EN ISO 11654	C
Surface [m ²]	11,90
Installation method	RMA 500/100
Density [kg/m ³] accord. to ISO 845	9 (+2/-1)
Fire behaviour accord. to DIN 4102	B1
Fire behaviour accord. to EN ISO 13501	B - s1, d0



Practical Sound absorption coefficient α_p according to UNE-EN ISO 11654

Freq. [Hz]	125	250	500	1.000	2.000	4.000
α_p	0,20	0,45	0,85	1,00	1,00	1,00



SKUM ACOUSTICS SL
T. : +34 93 119 03 54
@ : info@skumacoustics.com
www.skumacoustics.com