

Sound absorption coefficient according to UNE-EN ISO 354, UNE-EN ISO 11654, ASTM C 423

Determination of sound absorption coefficients

Manufacturer : Skum Acoustics SL
Brand : Skum Acoustics

Product ref. : JJM080
Date : 11.02.2019

Description of the acoustic element :



Material : -
Thickness [mm] : 80
Notes : -

Format [mm] : -
Color : -

Evaluation : Reverberation time
Other values obtained by engineering method

Frequency [Hz]	Absorption coeff. α_s	Equiv. Area A
100	0,15	1,49
125	0,24	2,47
160	0,33	3,39
200	0,53	5,45
250	0,62	6,37
315	0,79	8,12
400	0,92	9,46
500	0,92	9,41
630	0,95	9,71
800	0,96	9,82
1.000	0,96	9,87
1.250	0,96	9,82
1.600	0,97	9,97
2.000	0,97	9,97
2.500	0,99	10,18
3.150	0,99	10,13
4.000	1,01	10,33
5.000	1,02	10,49

NRC	0,85
SAA	0,88
α_w	0,95
Sound Absorption Class accord. to UNE-EN ISO 11654	A
Surface [m ²]	10,28
Installation method	E000
Density [kg/m ³] accord. to ISO 845	-
Fire behaviour accord. to UNE 53127	-
Fire behaviour accord. to EN ISO 13501	-



Practical Sound absorption coefficient α_p according to UNE-EN ISO 11654

Freq. [Hz]	125	250	500	1.000	2.000	4.000
α_p	0,25	0,65	0,95	0,95	1,00	1,00



SKUM ACOUSTICS SL
T. : +34 93 119 03 54
@ : info@skumacoustics.com
www.skumacoustics.com